



PCT/GB 00 / 02584

00/031501



#2

INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

REC'D 10 AUG 2000

GB 00/02584


4

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

Dated 28 July 2000

**PRIORITY
DOCUMENT**


SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

THIS PAGE BLANK (USPTO)

THIS PAGE BLANK (USPTO)

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)



The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

1. Your reference RRS/7237

2. Patent application number

(The Patent Office will fill in this part)

9916601.9

3. Full name, address and postcode of the or of each applicant (underline all surnames)

Biocomposites Limited
Etruscan Street, Etruria, Stoke-on-Trent, Staffordshire, ST1 5PQ, England

Patents ADP number (if you know it)

7408917001

If the applicant is a corporate body, give the country/state of its incorporation

United Kingdom

4. Title of the invention

Calcium Sulphate

5. Name of your agent (if you have one)

Swindell & Pearson

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

48 Friar Gate,
Derby DE1 1GY

Patents ADP number (if you know it)

00001578001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

Yes

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description 7

Claim(s)

Abstract

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*)

Request for substantive examination (*Patents Form 10/77*)

Any other documents
(please specify)

11. I/We request the grant of a patent on the basis of this application

Signature Swindell + Pearson Date 15th July 1996
Swindell & Pearson

12. Name and daytime telephone number of person to contact in the United Kingdom
Mr. R. R. Sales
Derby (01332) 367051

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- a) *If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505*
- b) *Write your answers in capital letters using black ink or you may type them.*
- c) *If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.*
- d) *If you have answered 'Yes' Patents Form 7/77 will need to be filed.*
- e) *Once you have filled in the form you must remember to sign and date it.*
- f) *For details of the fee and ways to pay please contact the Patent Office.*

Calcium Sulphate

This invention concerns a method of producing surgical grade calcium sulphate and particularly but not exclusively a method of producing a resorbable osteoconductive bone void filler material.

Plaster of paris (hemi-hydrate calcium sulphate) is known to be suitable for use as a filler for bone defects. This material provides a number of required characteristics and does not produce any significant undesirable reaction within a body. Traditionally plaster of paris is produced from naturally occurring gypsum. This often has associated undesirable impurities. For medical applications and particularly for implantation high purity materials are obviously needed. Whilst it is possible for calcium sulphate to be produced synthetically, conventional techniques produce a material which has a high surface area which thus has a high water demand and therefore produces a low strength material when set. Such set material has a high dissolution rate and too short a residence time when implanted.

Plaster of paris, or more accurately calcium sulphate, has two modes of use as a bone filler. The first is in the di-hydrate form, usually as pellets which can be placed in a bone void. The second is as a hemi-hydrate powder which can be made up with water into a paste, which paste is mouldable to a required shape. Such materials are usable in the fields of orthopaedic, dental and maxillofacial surgery. Hemi-hydrate calcium sulphate has two forms. The first α is produced by hydrothermal treatment of the di-hydrate. The second β is produced by dry heat calcination. This latter form tends to have a low density, a higher water demand and therefore a lower strength and a faster dissolution rate than the α form.

According to the present invention there is provided a method of producing surgical grade calcium sulphate, the method comprising forming an initial calcium sulphate di-hydrate from synthetic constituents; dehydrating the

initial calcium sulphate di-hydrate to form calcium sulphate anhydrite; and subsequently rehydrating the calcium sulphate anhydrite and allowing subsequent calcium sulphate di-hydrate to crystallise out.

The subsequent di-hydrate may be used as a solid material bone filler and may be formed into pellets. The crystallised subsequent calcium sulphate di-hydrate may be ground prior to forming into pellets

Alternatively, the subsequent calcium sulphate di-hydrate may be calcined to form calcium sulphate hemi-hydrate, which material can be mixed with water or a salt solution to form a settable paste.

The calcining may be hydrothermal to form α calcium sulphate hemi-hydrate, and may be carried out in an autoclave. The calcining may be carried out at a pressure of 1-6 bar, and desirably 2-3 bar. The calcining is preferably carried out for a half to five hours, and desirably one to two hours.

Alternatively, the calcining may be carried out in dry heat conditions. The calcining may be carried out at a temperature of 70 - 200°C and desirably at 150 - 175°C, and for a period of a half to six hours and desirably one to two hours.

Following calcining, the calcium sulphate hemi-hydrate is preferably ground to a powder, and desirably with a particle size of less than 150 microns.

The initial calcium sulphate di-hydrate may be formed by mixing soluble calcium and sulphate salts such that calcium sulphate precipitates out. The di-hydrate thus formed may be washed, and subsequently filtered, crushed and/or dried.

The calcium salt may be a chloride or nitrate. The sulphate may be a sodium, potassium or ammonium salt. The calcium and sulphate salts are preferably provided in a substantially equal molecular ratio.

Alternatively the initial calcium sulphate di-hydrate may be formed from neutralising lime with sulphuric acid.

The dehydration of the initial calcium sulphate di-hydrate preferably takes place within a temperature range 110 - 350° and desirably at less than 300°C, to form soluble calcium sulphate anhydrite. Alternatively the ~~dehydration may take place at a temperature above 350°C to form insoluble~~ anhydrite.

The rehydration of the calcium sulphate anhydrite preferably takes place immediately following dehydration. The calcium sulphate anhydrite is preferably fully immersed in water or an aqueous solution for rehydration.

The rehydration may take place in water or a weak salt solution. The salt solution may comprise succinic acid or a potassium sulphate solution, with a concentration of less than 1% and desirably substantially 0.1%.

Finely powdered calcium sulphate di-hydrate may be added during rehydration such that the powdered calcium sulphate acts as crystal seeds, and the addition may be in the order of 5g per litre of water. For soluble hydrite the rehydration preferably takes less than five days.

The subsequent calcium sulphate di-hydrate is preferably dried following crystallisation. Alternatively, if it is to be autoclaved to form α hemi-hydrate it may be held in a damp condition.

Examples of the present invention will now be described by way of example only.

Example 1

4 moles of analytical grade potassium sulphate were dissolved in 2 l of deionised water. The resulting solution was added to a solution of 4 moles

calcium nitrate in 2 l of deionised water. The precipitate so formed was washed free of all nitrate and filtered on a Buchner Funnel followed by a further wash on filter with 100ml of deionised water. The resultant filter cake was dried at 40°C. Its BET SSA (specific surface area measurement) was determined as 0.61 m²/gm.

~~500 gms of this calcium sulphate di-hydrate filter cake were lightly~~ crushed, put into a 2 l borosilicate glass beaker, and placed in an oven at 200°C for 24 hours. On removal from the oven, 500 mls of deionised water - were added immediately to the beaker ensuring that all of the powder was immersed. This was allowed to soak for a period of 3 days, and then all supernatant liquid was drained away.

The resulting di-hydrate had a BET SSA of 0.06m²/gm. This coarse textured, granular, recrystallised di-hydrate was now placed in a stainless steel tray and autoclaved at 2.5 bar for a period of 2 hours. The α hemi-hydrate so formed was dried at 110°C for half hour prior to crushing in a pestle and mortar to pass a 150 micron mesh sieve.

The material so formed could be blended with 0.35 parts of water to form an easily workable and mouldable paste which became firm after 6 minutes and set to a hard, dense mass soon after.

This material blended with 0.35 parts of a 0.5% potassium sulphate solution formed an easily workable and mouldable paste which became firm after 3 minutes, and set to a hard dense mass soon after.

Example 2

~~500 gms of the precipitated calcium sulphate di-hydrate from Example 1~~ were put into a glass beaker, which was placed in an oven at 200°C for 24 hours. On removal from the oven, 500 mls of 0.1% succinic acid solution were added to the beaker, ensuring that all of the powder was immersed. This was soaked for

16 hours, at which time the supernatant liquid was drained away to reveal a coarse textured recrystallised gypsum powder.

This powder was treated hydrothermally as in Example 1 above, followed by drying and crushing.

~~The resulting α hemi-hydrate was blended with 0.45 parts of water to~~
form a paste which became firm after 6 minutes and set to a hard, dense mass soon after.

Example 3

500 gms of the precipitated calcium sulphate di-hydrate from Example 2 were calcined in an oven at 400°C for 2 hours. The anhydrite so formed was the orthorhombic or so called dead burned variety. This was removed from the oven, immersed in deionised water and allowed to soak for a period of 14 days. The supernatant liquid was drained away to reveal a coarse, gritty recrystallised gypsum powder. This was hydrothermally treated in an autoclave for 2½ hours at 1.7 bar. The resulting α hemi-hydrate was dried at 110°C and crushed to pass a 125 micron mesh sieve. This gave a material which was blended with 0.38 parts of sterile, deionised water to form a mouldable paste which became firm 5 minutes after mixing, and set to a hard mass soon after.

Example 4

Recrystallised di-hydrate prepared according to Example 1 was dried at 40°C overnight. The dried material was crushed to pass a 150 micron mesh sieve and the resulting fine powder was heated in a shallow stainless steel tray at a depth of 2 cm for 2 hours at 165°C. The hemi-hydrate so formed was of the β variety, and was blended with 0.65 parts of sterile deionised water to form a mouldable paste which set to give a firm mass.

Example 5

500gms of the precipitated calcium sulphate di-hydrate from Example 1 were put into a glass beaker, which was placed in an oven at 150°C for 40 minutes. On removal from the oven, the resultant β hemi-hydrate was added to ~~600ml of deionised water and mixed to form a fluid mass. This was poured~~ into a shallow stainless steel tray and allowed to re-hydrate and set. The following day the set gypsum in the stainless steel tray was put into an oven at 250°C for 20 hours to allow for complete dehydration. The resulting calcium sulphate anhydrite was covered with deionised water and allowed to soak for a period of 4 days and then all supernatant liquid was drained away to reveal a coarse textured recrystallised gypsum powder. This powder was treated hydrothermally as in Example 1 above to produce an α hemi-hydrate.

Summary

Example 3 shows that the insoluble anhydrite requires a much longer crystallisation time than the soluble variety. Example 4 shows the use of dry heat calcination to produce the β hemi-hydrate. It has been found that using a salt for the rehydration speeds up the process, as is illustrated in Example 2. Finely powdered gypsum may be added to act as crystal seeds.

Example 5 shows that the synthetic precipitated calcium sulphate di-hydrate can first be formed into a hemi-hydrate followed by re-hydration with a minimum quantity of water to form a set mass of di-hydrate. This set di-hydrate can then be dehydrated and recrystallised as previously described.

The above examples describe production of calcium sulphate hemi-hydrate which can be formed into a paste. ~~The α hemi-hydrate thus formed can~~ be blended with 0.30 to 0.40 parts water or saline solution to give a mouldable paste which sets to a firm mass. The β hemi-hydrate requires 0.55 to 0.70 parts water to form an appropriate paste.

If the calcium sulphate is required to be used in a pellet form, the calcination from the di-hydrate to the hemi-hydrate is not required. The subsequent di-hydrate would be ground or crushed and formed into pellets of an appropriate size.

There is thus described a method of producing surgical grade calcium sulphate which combines the advantages of the synthetic route with the characteristics encountered with naturally occurring gypsum. The method is relatively straightforward and can thus be readily reproduced, and without significant extra costs.

Various modifications may be made without departing from the scope of the invention. For example, the initial di-hydrate may be formed by neutralising lime with sulphuric acid. Other materials such as calcium chloride or sodium sulphate, may be used to form the initial calcium sulphate. Other salts may be used during the process as is required. Other conditions may be applicable to the dehydration, rehydration or calcining.

Whilst endeavouring in the foregoing specification to draw attention to those features of the invention believed to be of particular importance it should be understood that the Applicant claims protection in respect of any patentable feature or combination of features hereinbefore referred to and/or shown in the drawings whether or not particular emphasis has been placed thereon.

PCT NO. 06/01 0250

Form 73, 26 7.00

Agent: Simdala & Associates

THIS PAGE BLANK (USPTO)
